COMPARISON OF THE PHOTOGRAPHY, RADIOGRAPHY AND PROCESSED IMAGES IN THE STUDY OF METALLIC PIECES FROM ARCHAEOLOGICAL SITES

Jose A. Madrid^{a,*}, Effat Yahaghi^b, Jose M. Melchor^c, Amir Movafeghi^d

^a Instituto Universitario para la Restauración del Patrimonio, Universitat Politècnica de València, Camino de Vera s/n, 46022 Valencia, Spain. jmadrid@crbc.upv.es

^b Department of Physics, Imam Khomeini International University, Qazvin, Iran. yahaghi@sci.ikiu.ac.ir

^c Museo Arqueológico, Ayuntamiento de Burriana, Plaza de la Merced s/n, 12530 Burriana, Spain. arqueologo@burriana.es

^d Nuclear Science and Technology Research Institute (NSTRI), Tehran, Iran. amovafeghi@aeoi.org.ir

Abstract:

Archaeologists and conservators face different challenges when inspecting metal pieces extracted from the archaeological sites including their high quantity and the complexity of the materials and their shapes and often the pieces are covered by oxidized layers. Non-destructive analysis techniques such as digital radiography imaging are used to efficiently detect and classify the pieces. Furthermore, the shape of pieces, the state of their metalcore is assessed to inform the required handling, investigation, and intervention technique. However, for thicker metal pieces, the acquired X-ray images are often foggy and lack the required quality making the effective assessment of the piece difficult. Without further tools at the disposal of the non-radiologically-trained archaeologists and conservators, extraction of accurate information from unprocessed radiographs showing the internal hidden structures, the level of oxidation, and the presence of cracks is not possible. To complement the visual examination and original radiograph of the piece, an effective solution for improving the contrast of pertinent features of the x-ray image is implementing a digital imaging processing algorithm to enhance the quality of the radiographs. This study has used the "Fast 2D Gaussian convolution first-order infinite impulsive response" (IIR) to extract greater detail for better interpretation of the radiological images. The archaeological metal pieces to which the complementary technique was applied were from two important Iberian-Roman sites located on the coast of the municipality of Burriana (Castellón), i.e. Sant Gregori and Torre d'Onda. The pieces were the property of the archaeological museum of Burriana, Spain, and were investigated using X-ray imaging. The complexity of the task necessitated close interaction between the multidisciplinary team involved in this study. The study has found that the combination of visual inspection/photograph, the original radiograph, and processed X-ray image is a powerful inspection tool especially in the hands of the non-radiologically trained archaeological experts and conservators. The complementary technique of using processed X-ray images was also found to be highly effective for quantification of the location, geometry, and extent of the pertinent features of the studied items as confirmed by the experts involved in this study.

Keywords: digital radiography, metal pieces, archaeology, conservation, Sant Gregori, Torre d'Onda, The Archaeological Museum of Burriana

1. Introduction

As a non-destruction method, Radiography testing (RT) offers several advantages for examining metal archaeological pieces. Such items are usually covered in earth and have extensive surface oxidation limiting effective visual inspection. RT is often the technique of choice therefore for the examination of such items with digital RT offering further data analysis and processing possibilities (Fell, Mould, & White, 2006; Nicoll & Hook, 2008; Madrid & Ramírez, 2011; Madrid, 2014a; Lang & Middleton, 2016).

Flemish Institute for the Archaeological Heritage reports that with conventional tools it would take about 24 years to clean the total of 25,000 pieces of iron from an archaeological site; the process was reduced to two and a half years with the aid of RT.

Cleeren (2006) report that using RT they could focus on two-thirds of items that were partial "diagnostically cleaned". Caple and Garlick (2018) however reported that that reliance only on a digital comparison of RT images was found to be too subjective for the assessment of the object.

* Corresponding Author: Jose A. Madrid, jmadrid@crbc.upv.es

The archaeological site of Sant Gregori was excavated for the first time in 1987. At the time of the initial archaeological survey, little was known about the site; for example, unlike similar villa sites in the same vicinity, the new site had been built with luxurious characteristics.

Further recent excavation effort was commissioned as a result of a new urbanization project in the area. The area of the settlement was delimited and later a series of surveys were carried out at specific locations to reveal the state of conservation of the remains and their characteristics.

Later a series of archaeological campaigns were undertaken which revealed that the town had two distinct phases of settlement. Relating to the initial settlement phase, the excavation revealed the presence of a funerary monument, a peristyle with a large rectangular pond, around which a series of rooms and thermal baths are arranged.

The second phase dated from the 2nd century AD. It was characterized by the reform and reuse of part of the existing structures. The funerary monument had been razed, the existing rooms were compartmentalized and new flats were built with smaller walls. The second phase of settlement was generally a period of less wealth (Ferrer, Melchor, & Benedito 2013).

With the selection of pieces from the site of the Roman Villa of Sant Gregori (Díaz, 2014), 66 radiographs were produced, which revealed the interior of 278 metal fragments, of which 149 were nails according to the classification by typologies where Manrique (1980) makes on the nails found in a deposit in Numancia (Soria) constituting about 53% of the items. The rest of the pieces were staples, rings, or knife fragments. On that occasion, the study provided information on the contours of the pieces, the distinction of their morphology, and facilitated the cleaning work to which the pieces were subjected.

The study of the pieces from the Torre D'Onda site was poorly documented as it was greatly affected by the construction of numerous houses and the promenade. The restricted nature of the excavated area only allowed broad confirmation of the existence of a first enclave from the 6th or 7th century B.C., perhaps associated with the end of the Iron Age.

The most important settlement was from the Iberian-Roman era, specifically from the 3rd century B.C., where very homogeneous levels were documented that included large containers such as amphorae, kalathoi, pots, jars, small vessels, remains of elements of iron, lead, fauna, etc. Abundant ceramics were excavated from Campania where only large foundation structures were found. The fragments analyzed here were recovered during archaeological campaigns carried out between 1977 and 2007.

This settlement is thought to be related to the coastal trade in Iberian and Roman-Republican times, practically disappearing at the beginning of the imperial era due to the large Roman owners with interests in the viticulture of Hispania Citerior, who altered the commercial circuits and the system of exploitation of the territory (Melchor, 2013).

On this occasion, 32 radiographs were obtained relating to 193 objects (Aznar, 2020). Making the same typological discrimination as the previous case (Manrique, 1980), 54

nails were revealed which constituted about 29% of the objects. The sets were spikes or hooks.

The two sets of items share some common archaeological characteristics since they come from wide strata of occupation and present a post-depositional mixture of various periods or cultural stages. Neither of the sets has previously been subjected to any conservation or restoration processes.

2. Objectives

In this study, enhanced radiography has been used to make a detailed and quantitative assessment of the objects' state of conservation, especially of their metallic core.

Radiography enhancement has been achieved through the application of image processing based on Fast 2D Gaussian convolution first-order infinite impulsive response (IIR) to improve both the contrast and the contouring on the Database Administration System (DBAS).

3. Methodology

Photographic and radiographic images were analyzed for each item and the processed image was used to provide further complimentary information. The multi-disciplinary team included the Laboratory of Documentation and Registration at the University Institute for the Restoration of the Patrimony (IRP) of the Universitat Politècnica de València (UPV) for the acquisition of documentary and radiographic registration of information and the Imam Khomeini International University (Qazvin, Iran) for enhanced processing of the X-ray images.

3.1. Photographic and radiological experiments

The initial step of the study involved the systematic documentation of information for all the pieces. Pieces were grouped and assemble mounted on rigid plates ready for deployment of the radiographic plate. The plates had a scale system and signage references (Fig. 1). The mounting system allowed reproducible geometric set-up for the pieces. The photographic image was taken in the visible light spectrum on a Kaiser® RS10 Copy Stand Using a reflex-type camera, Canon® EOS 15 (Fig. 2).

Figure 1: A Set of studied objects.

Figure 2: Photography process on a table type Kaiser® RS10 Copy Stand.

The X-ray unit was the TRANSPORTIX 50 from the General Electric® company which had a 3 kW X-ray tube, a 2.3 mm focal spot size with a total filtration of 2 mm of aluminum (Fig. 3). The equipment allowed the acquisition of images between 20 kV and 110 kV (Madrid, 2014b). The Tube current was set to 10 or 20 mA depending on the thickness of the item.

Figure 3: X-ray imaging set up.

The system for centering and locating the imaging area was achieved using visible light collimation. The system also had a duplex-type Image Quality Indicator (IQI) compliant with ISO 19232-5 standard supplied by Kowotest®. The CR MDT4.0T chassis, from AGFA®, was adjusted to 35 cm by 43 cm format and a 3480 × 4248 pixel matrix was set for the radiographic images.

Nine pieces from both the Sant Gregori (ref_303, ref_308, ref_310, ref_321 and ref_325) and Torre d'Onda (ref_894, ref_895, ref_906 and ref_910) sites were selected for radiography as referenced in Table 1.

Table 1: Parameters used in radiography

Ref.-Rx	Voltage (kV)	Intensity (mA)	Exposure (sec.)
ref_303	72	20	3
ref_308	72	20	3
ref_310	74	20	3
ref_321	60	20	3
ref_325	60	20	3
ref_894	75	20	3
ref_895	75	20	3
ref_906	75	20	3
ref_910	75	20	3

The kV was varied as necessary but the current was set to 20 mA with a time maintained at 3 sec. and the source to the detector was set to 100 cm for all exposures.

For items ref_303 to ref_310, the tube voltage was set to 72 kV but for items ref_321 and ref_325, this was reduced to drop to 60 kV since the corrosion layer was small in the former and excess soil had adhered to the latter item. For items ref_894 to ref_910, the tube voltage was set to 75 kV.

The CR plate was processed using a computerized radiography workstation for indirect radiography with CR 30-X digitizer, from AGFA®. The procedure was controlled by AGFA® NX quality control and image identification program.

This working protocol allowed comparison between both image records, where the scale values were kept constant for all radiographic acquisition, see Figures 4a and 4b.

Figure 4: Comparison between photographic and radiographic images at ref_895: a) Photographs; b) radiographs.

The criteria used for the selected pieces that were applied to the image enhancement process were determined by the characteristics of the items, mainly their topological complexity, Table 2.

Table 2: Provisional description of objects.

Ref.-Rx	Provisional description and reason for selection
ref_303_y4_1	Fibula bridge fragment; The piece has a "T" shape that makes it unusual
ref_303_y4_2	Fibula bridge fragment; The piece has a cross shape that makes it unusual
ref_308_y8_1	Handle; Its shape would indicate that it is part of a larger and more complex artifact
ref_310_y10_1	Decorative rivet; A priori, it looked like a rivet or nail, but the hemispherical shape of the head is very rare at the site
ref_321_y21	A possible part of a bolt; The shape of its circular tip indicates that it would be an instrument of complex shape
ref_325_y25	Linear element possibly disabled by twisting; It was a very complex form of indeterminate interests due to its unique appearance
ref_894_1	Fragment of a large square or rectangular plate with possible rivets; It is the largest iron fragment recovered in the archaeological site
ref_895_4	Iron tape with other metal rivets, possible decorative element; This is the best-preserved piece with apparent rivets on the site
ref_906_1	Element with the tip for the sleeve, possible projectile or punch; It was one of the few fragments of unknown shape that had to be identified
ref_910_1	Elbow-shaped element; It was one of the few fragments of unknown shape that has to be identified

The output of the CR scanning system was in DICOM® standard but needed to be changed to enable data handling in the processing software. Considering that the proposal is a proof of concept of the system used, the file characteristics were set to yield high compatibility. The final images were 800 × 600 pixels and in sRGB color system with a color depth of 8 bits.

3.2. Fast 2D Gaussian convolution

In this study, Fast 2D Gaussian convolution first-order infinite impulsive response (IIR) approximation was used to enhance the contrast and edges of the images using shock filters (Weickert, 2003) and anisotropic diffusion (Perona & Malik, 1990). In simpler format the 2-D image; $I(i,j)$; discrete Gaussian convolution can be written as (Álvarez & Mazorra, 1994) Eq. (1):

$$u(i,j) = h_{\sigma}(i,j) * I(i,j) = \sum_k \sum_l h(i-k, j-l) I(k,l) \quad (1)$$

where "*" denotes convolution operator and $h_{\sigma}(i,j)$ denotes the Gaussian mask or kernel with σ standard deviation and defined as follows in Eq. (2):

$$h_{\sigma}(i,j) = \frac{1}{(2\pi\sigma^2)^{\frac{m}{2}}} e^{-\frac{i^2+j^2}{2\sigma^2}} \quad (2)$$

Since the m-dimensional kernel $h_{\sigma}(i,j)$ has a 'bell-shaped curve' and drops-off rapidly to infinity, one can use discrete Gaussian convolution with the sampled and normalized kernel. Algorithm 1 shows the procedure of the general Gaussian-based convolution used in this study.

Algorithm 1: Gaussian-based convolution.

-
1. Initialization
 - a. Input noisy image $I \in \mathbb{R}^{K \times L}$
 - b. Set the noise standard deviation σ
 - c. Input the Gaussian kernel h_{σ}
 2. Processing

For $j = 0: L - 1$ do
 $(u_{i,j})_{i=0}^{K-1} \leftarrow h_{\sigma} * (f_{i,j})_{i=0}^{K-1}$
 End for
 For $i = 0: K - 1$ do
 $(u_{i,j})_{j=0}^{L-1} \leftarrow h_{\sigma} * (f_{i,j})_{j=0}^{L-1}$
 End for
 End
 3. Generate Processed image: $u = h_{\sigma} * f$
 4. Generate Final Image
 - a. Subtract the original radiograph from the processed image
 5. End
-

In Algorithm 1, the 2-D Gaussian convolution is considered a tensor product of 1-D convolution. These algorithms convolve data with an approximation of a Gaussian with a standard deviation sigma and the number of steps. The routine used the fast Gaussian convolution algorithm of Álvarez and Mazorra (1994), where the Gaussian has been approximated by a cascade of first-order infinite impulsive response (IIR) filters according to the heat equation. The calculated filters were applied along with columns and rows in each step.

The boundaries were handled with a half-sample symmetric extension. Using more steps increased the accuracy but also prolonged the computation time. Increasing the σ will make the output images smoother for the proposed convolution algorithms. Finding the optimal value of σ was difficult due to the different levels of the fogginess of each radiograph. Therefore, the foggy components were subtracted from the original images to yield the sharpened images.

The algorithms were run in the Matlab 2016 software with an Intel® Core-i7 based computer (MathWorks, 2021).

4. Results and discussion

In this study, some metallic pieces from the archaeological sites have been investigated for estimating the metal core and the corrosion layer of oxidation. For this purpose, the X-ray imaging method was used to reveal the hidden layer without any damage to pieces. Then, the Fast 2D Gaussian convolution first-order infinite impulsive response (IIR) is implemented to the radiography images for improving the contrast and better information extraction.

Figures 5a, 5b, and 5c show the photograph, radiograph, and the reconstructed image for item ref_303_y4_1

respectively. The images are annotated with the arrow to indicate the location of the piece's advanced corrosion.

Figure 5: Study of metallic pieces: a) photograph image; b) radiographic image; c) processed image of ref_303_y4_1.

Items ref_303_y4_2, Figure 6a, and ref_906_1, Figure 7a, exhibit severe loss of metallic core as shown on the processed images Figures 6b and 7b, where layers of corrosion have led to partial disintegration of the items as indicated on the images.

Figure 6: Study of metallic pieces: a) Photograph image; b) processed image of ref_303_y4_2.

Figure 7: Study of metallic pieces: a) Photograph image; b) processed image of ref_906_1.

Similarly, Figure 8a, 8b, and 8c relate to item ref_308_y8_1. The extent of oxidation with the fracture lines are better visualized in the processed image such as those shown in comparison to the original radiograph; for example, marker 'a' shows the edge has fractured along the piece, and marker 'b' shows the state of exfoliation in its midsection.

Figure 8: Study of metallic pieces: a) Photograph image; b) radiographic image; c) processed image of ref_308_y8_1.

The enhancement of image contrast in the processed image is invaluable to the radiographically untrained eyes so the archaeologist can focus on the areas of most interest through the elimination of noise/fog and non-pertinent information content. The level of the fissure and the degree of exfoliation are decisive data in intervention works for correct storage.

Figure 9b and 9c show similar images for the decorative rivet ref_310_y10_1. Simultaneous review of the three images by the operator whilst working on the piece would help inform the choice of the cleaning method e.g. to use a mechanical versus chemical method. In this example, the radiograph is foggier due to the greater thickness of the core metal. Image processing has helped remove much of the fogginess to yield enhanced contrast in the regions of interest.

Figure 9: Study of metallic pieces: a) Photograph image; b) radiographic image; c) processed image of ref_310_y10_1.

A statement that we can see better again in ref_910_1 (Fig. 10). The unknown region of the piece is marked by archaeologists (Fig.10a). The radiograph (Fig 10b) showed an elbow-shaped element in good condition. The processed image (Fig.10c) certified this information. A

comparison of the three images showed that both fragments belong to the same object.

Figure 10: Study of metallic pieces: a) Photograph image; b) radiographic image; c) processed image of la ref_910_1.

The processed image offers higher contrast in regions such as the boundary between concretion and the state of the metallic core, or the internal exfoliation regions. Figures 11a and 11b show the bolt fragment of item ref_321_y21 where the two pieces have become fused over time. Similarly, it can be seen that item ref_325_y25 has lost all its shape by torsion, Figures 12a and 12b.

Figure 11: Study of metallic pieces: a) Photograph; b) processed image of ref_321_y21.

Figure 12: Study of metallic pieces: a) Photograph image; b) radiographic image; c) processed image ref_325_y25.

Also, of potential significance is the enhanced results offered by the processed image of the items internal texture and porosity which informs the investigator of the manufacturing processes (Lang & Middleton, 2016; Yahaghi, Madrid, & Movafeghi, 2020), see Figures 13a and 13b relate to the metal fragment ref_894_1 where the processed image focuses on the internal granulometry of the fragment.

Figure 13: Study of metallic pieces: a) Photograph image; b) radiographic image; c) processed image of ref_894_1.

Similarly, for item ref_895_4, which corresponds to an iron tape with metal rivets which is thought to be from a decorative element, Figure 14a. The processed image shown in Figure 14b marks the perimeter of the piece that would otherwise be blurred out due to its advanced state of oxidation.

Figure 14: Study of metallic pieces: a) Photograph image; b) processed image of ref_895_4.

5. Conclusion

This study has found that the combination of visual inspection/photograph, the original radiograph, and tool than the photograph plus the radiograph alone. They complement each other and allow the operator to focus on the pertinent imaging data to better inform the intervention processes.

Furthermore, the pertinent information including the internal state of the piece, the metal core, and level of its oxidation and disintegration, the presence of exfoliated in inner layers, maybe better quantified in terms of the location, geometry and extent of the feature when the processed X-ray image is deployed as confirmed by the archaeological experts involved in this study.

With effective protocols, the extracted information can be used by the experts to direct the archaeological intervention where the maximum benefit would result whilst shielding the piece from unnecessary damage during the process and ensuring.

Acknowledgements

We are grateful to all the institutions involved in this multidisciplinary work, including the archaeological museum of Burriana (Spain), the Laboratory of Documentation and Registration in the University Institute for the Restoration of the Patrimony (IRP) of the Universitat Politècnica de València (UPV) and Imam Khomeini International University (Qazvin, Iran), who have made available to us both the means and the archaeological pieces.

References

- Álvarez, L., & Mazorra, L. (1994). Signal and Image Restoration using Shock Filters and Anisotropic Diffusion. *SIAM J. on Numerical Analysis*, 31(2), 590–605. <https://doi.org/10.1137/0731032>
- Aznar, C. (2020). *Valoración global de objetos metálicos arqueológicos a través de los rayos x. Estudios previos de los materiales metálicos de Torre d'Onda (Burriana, Castellón)*. Trabajo fin de Máster. Universitat Politècnica de València. <http://hdl.handle.net/10251/150821>
- Caple, C., & Garlick, V. (2018). Identification and valuation of archaeological artifacts: developments using digital X-radiography. *Journal of the Institute of Conservation*, 41(2), 128–141. <https://doi.org/10.1080/19455224.2018.1464487>
- Cleeren, N. (2006). Oudenburg: conservatie is (gefundeerde) keuzes maken, Conservering van objecten versus de conservering van hun wetenschappelijke inhoud. *Journée d'archéologie romaine. Gent: Flemish Institute for the Archaeological Heritage*, pp.140–145.
- Díaz, T. (2014). *Propuesta metodológica en el estudio previo de los materiales féreos de la Villa romana de Sant Gregori (Burriana, Castellón). Aplicación de la técnica radiográfica digital en las fases previas al proceso de restauración*. Trabajo fin de Máster. Universitat Politècnica de València. <http://hdl.handle.net/10251/39213>
- Fell, V., Mould, Q., & White, R. (2006). *Guidelines on the X-radiography of Archeological Metalwork*. Swindon: English Heritage.
- Ferrer, J. J., Melchor, J. M., & Benedito, J. (2013). Sant Gregori. Un complejo arquitectónico de época romana en la costa de Burriana (España). *Millars: espai i història*; 36, 201–225. <http://dx.doi.org/10.6035/Millars>
- Lang, J., & Middleton, A. (2016). *Radiography of Cultural Material*. Londres, Reino Unido: 2nd ed, Elsevier Butterworth-Heinemann.
- Madrid, J. A. (2014a). Catálogo radiográfico del Servicio de Rayos X del Laboratorio de Documentación y Registro. *Arché*, 8, 87–98. <http://hdl.handle.net/10251/85227>
- Madrid, J. A. (2014b). Dos décadas de inspección radiográfica en España: retrospectiva y horizontes futuros en un contexto de cambio tecnológico. Intervención. *Revista Internacional de Conservación, Restauración y Museología, Escuela Nacional de Conservación, Restauración y Museografía-INAH*, 10, 87–95.
- Madrid, J. A., & Ramírez, A. (2011). Radiografía digital en el estudio de piezas cerámicas. Estudio e interpretación de cerámica medieval procedentes del Museo Arqueológico Municipal de Burriana. En J. M. Melchor, J. Benedito, T. Pasies (Eds.), *La arqueología de la Buriyyana islámica a la Borrianacristiana*, (pp. 153–172). Valencia, España: Conselleria de Governació de la Generalitat Valenciana.
- Manrique, M. (1980). *Instrumentos de hierro de Numancia conservados en el Museo Numantino (Soria)*. Madrid, España: Ministerio de Cultura.
- MathWorks. (2021). MATLAB - El lenguaje del cálculo técnico - MATLAB & Simulink (mathworks.com). Retrieved March 15, 2021, from <https://es.mathworks.com/products/matlab.html>
- Melchor, J. M. (2013). *Diez años del Servicio Arqueológico Municipal de Burriana (2003-2013)*. Burriana, España: Ayuntamiento de Burriana.
- Nicoll, D., & Hook, A. (2008). *Saracen Strongholds AD 630-1050: The Middle East and Central Asia*. Oxford, Reino Unido: Osprey Publishing.
- Perona, P. & Malik, J. (1990). Scale-space and edge detection using anisotropic difusión. *IEEE Transactions on Pattern Analysis and Machine Intelligence*, 12(7), 629–639.
- Weickert, J. (2003) Coherence-Enhancing Shock Filters. In: Michaelis B., Krell G. (eds) *Pattern Recognition. DAGM 2003. Lecture Notes in Computer Science*, 2781. Springer, Berlin, Heidelberg. https://doi.org/10.1007/978-3-540-45243-0_1
- Yahaghi, E., Madrid, J. A., & Movafeghi, A. (2020). Fracture and internal structure detection of ceramic objects using improved digital radiography images. *Journal of Cultural Heritage*, 44, 152–162. <https://doi.org/10.1016/j.culher.2020.02.003>